

Chongqing Polycomp International Corp.

Jianqiao Industiral Park B, Dadukou District Chongqing, China.

Post code: 400082 website: www.cpicfiber.com

Technical support . Tel: (+86-23)68157743 (+86-23)68157178

Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586

Fax: (+86-23)68157822

Chopped Strand for PPS ECS309C

Identification

Example: ECS309C-3-H

ECS: E-glass Chopped strands

Sizing code: 309C

Chopped length (mm): 3 Filament diameter: 10



Product Description

Standard products for PPS, suitable for amorphous PPA, with water resistance properties. Applied in automobile and electric products. NPE free.

Product Benefits

- Unique surface treatment technology
- Good dispersion
- Good water resistance
- Good operability process
- Good resin bond

Technical Characteristics

Sizing type	Diameter (µm)	Moisture Content (%)	LOI(%)	Bulk Density (g/ cm3)
/	ISO 1888	ISO 3344	ISO 1887	ISO 15100
Silane	±1	≤0.05	0.35±0.1	0.65±0.15

Product code	Glass Type	Filament diameter[µm]	Chopped length [mm]
ECS309C	ECT	10	3



Chongqing Polycomp International Corp.
Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

Packing

Packing	Weight [kg]	Bag number per pallet	Palletsize [mm] length*width*height
super-sack	1000	1	1140*1140*1100
paper bag	25	40	850*500*120

Pallets illustration



Note: Products can be packed according to the customer's request.

Storage

- If no special requirements, it should be stored in cool and dry place. It is recommended that the temperature control in the 10-30°C, moisture control in 50-
- This product before use should always be placed under the sealed packaging.
- Pallet stacking height should not be more than one layer.





