

Chongqing Polycomp International Corp. Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

# ECS305K

#### Identification

Example:	ECS 305K-3
E:	Boron Free E – Glass
305K :	CPIC sizing reference
CS:	Chopped Strands
3:	Chopped length (mm)



## **Product Description**

Standard product for PE and PP, excellent white color. Applied in automobile, electric products, daily use and build. FDA approval and NPE free.

### **Product Benefits**

- Unique surface treatment technology
- Good dispersion
- Excellent white color
- Good operability of the process
- Good resin bond

# **Technical Characteristics**

Sizing type	Filament Diameter (µm)	Moisture content (%)	Loss on ignition(%)	Integrity (g)
	ISO1888	ISO3344	ISO1887	*CPIC/TM-13
Silane	10±1	≤0.05	0.5±0.1	≤5

Product Code	Type of Glass	Filament Diameter (µm)	Chopped Length (mm)
ECS305K	E	13	3 / 4.5



## Packaging

Available in two packaging:

- 1. The bottom of the ease of unloading tons of polypropylene super sack bag
- 2. More flexible coated paper bags

# **Pallets characteristics**

Package	Weight (kg)	Bag number per pallet	Pallet size (mm)
Super sack bag	1000	1	1140*1140*1100
Coated paper bags	25	40	850*500*120





Note: Please contact us if you have special requirements.

### Storage

If no special requirements, it should be stored in cool and dry place. It is recommended that the temperature control in the 10-30°C, moisture control in 50-75%.

- This product before use should always be placed under the sealed packaging.
- Pallet stacking height should not be more than one layer.



