

Chongqing Polycomp International Corp. Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

ECS305B

Identification

Example:	ECS 305B-3		
E:	Boron Free E – Glass		
305B :	CPIC sizing reference		
CS:	Chopped Strands		
3:	Chopped length (mm)		



Product Description

Standard product for PE and PP, high mechanical and excellent white color. Applied in automobile, electric products, daily use and build. FDA approval and NPE free.

Product Benefits

- Unique surface treatment technology
- Good dispersion
- Excellent white color
- Super detergent resistance
- Good operability of the process
- Good resin bond

Technical Characteristics

Sizing type	Filament Diameter (µm)	Moisture content (%)	Loss on ignition(%)	Integrity (g)
	ISO1888	ISO3344	ISO1887	*CPIC/TM-13
Silane	13±1	≤0.05	0.5±0.15	≤5

Product Code	Type of Glass	Filament Diameter (µm)	Chopped Length (mm)
ECS305B	E	13	3 / 4.5



Packaging

Available in two packaging:

- 1. The bottom of the ease of unloading tons of polypropylene super sack bag
- 2. More flexible coated paper bags

Pallets characteristics

Package	Weight (kg)	Bag number per pallet	Pallet size (mm)
Super sack bag	1000	1	1140*1140*1100
Coated paper bags	25	40	850*500*120





Note: Please contact us if you have special requirements.

Storage

If no special requirements, it should be stored in cool and dry place. It is recommended that the temperature control in the 10-30°C, moisture control in 50-75%.

- This product before use should always be placed under the sealed packaging.
- Pallet stacking height should not be more than one layer.

