

Chongqing Polycomp International Corp.
Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

ECS306

Identification

Example: ECS 306-3

Boron Free E - Glass E: 306: CPIC sizing reference CS: **Chopped Strands** 3: Chopped length (mm)



Product Description

Standard product for MPPO (PPE). Applied in automobile and electric products. FDA approval and NPE free.

Product Benefits

- Unique surface treatment technology
- Good dispersion
- Good integrity
- Good operability of the process
- Good resin bond

Technical Characteristics

| Sizing type | Filament Diameter (µm) | Moisture content (%) | Loss on ignition (%) | Integrity (g) |
|-------------|------------------------------|----------------------|----------------------|---------------|
| | ISO1888 | ISO3344 | ISO1887 | *CPIC/TM-13 |
| Silane | 13±1 | ≤0.05 | 0.6±0.1 | ≤5 |

| Product Code | Type of Glass | Filament Diameter (µm) | Chopped Length (mm) |
|--------------|---------------|------------------------|---------------------|
| ECS306 | E | 13 | 3 |



Chongqing Polycomp International Corp.

Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

Packaging


Available in two packaging:

- 1. The bottom of the ease of unloading tons of polypropylene super sack bag
- 2. More flexible coated paper bags

Pallets characteristics

| Package | Weight (kg) | Bag number per pallet | Pallet size (mm) |
|-------------------|----------------|-----------------------------|------------------|
| Super sack bag | 1000 | 1 | 1140*1140*1100 |
| Coated paper bags | 25 | 40 | 850*500*120 |





Note: Please contact us if you have special requirements.

Storage

If no special requirements, it should be stored in cool and dry place. It is recommended that the temperature control in the 10-30°C, moisture control in 50-75%.

- This product before use should always be placed under the sealed packaging.
- Pallet stacking height should not be more than one layer.







