



Jianqiao Industiral Park B, Dadukou District Chongqing, China.

Post code: 400082 website: www.cpicfiber.com

Technical support . Tel: (+86-23)68157743 (+86-23)68157178

Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586

Fax: (+86-23)68157822

Chopped Strand for BMC ECS402S

Identification

Example: ECS402S-3-H

ECS: E-glass Chopped strands

Sizing code: 402S

Chopped length (mm): 3 Filament diameter: 10



Product Description

This kind is specially designed for BMC processing. Applied in break system

Product Benefits

- Well dispersion
- Good distribution
- Good Compatibility with basic resin
- Excellent mechanical properties

Technical Characteristics

| Compatible Resin | Diameter (µm) | Moisture Content (%) | Loss on Ignition (%) | Bulk Density (g/ cm3) |
|-------------------|---------------|----------------------|----------------------|--------------------------|
| / | ISO 1888 | ISO 3344 | ISO 1887 | ISO 15100 |
| Phenolic Resin | ±1 | ≤0.1 | 1.05±0.15 | 0.55±0.15 |

| Product code | Glass Type | Filament diameter[µm] | Chopped length [mm] |
|--------------|------------|--------------------------|---------------------|
| ECS402S | ECT | 10 | 3、6 |



Chongqing Polycomp International Corp.
Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

Packing

| Package Method | Package weight [kg] | Quantity | Pallet size [mm] Length*width*height |
|-----------------------|------------------------|----------|--|
| Super sack bag | 1000 | 1 pallet | 1140*1140*1100 |
| Poly-plastic film bag | 25 | 40 bags | 850*500*120 |

Pallets illustration



Note: Products can be packed according to the customer's request.

Storage

- If no special requirements, it should be stored in cool and dry place . The recommended temperature range is 10-30 °C, humidity should be 50 -75%.
- The product should be always kept package encapsulation before use.
- Pallet stacking height should not over 1 layer.







